

Search Purdue News

Google™ Custom Search

[Academics](#)

[Athletics](#)

[Community](#)

[General](#)

[Events](#)

[Faculty
& Staff](#)

[Outreach](#)

[Research](#)

[Student](#)

[Rankings](#)

New process is promising for hydrogen fuel cell cars

June 16, 2010

SHARE    

 [Print Version](#)



Arvind Varma, from left, Purdue University's R. Games Slayter Distinguished Professor of Chemical Engineering, postdoctoral researcher Hyun Tae Hwang and doctoral student Ahmad Al-Kukhun review data from a new process for storing and generating hydrogen to run fuel cells in cars and portable consumer electronics. The process, called hydrothermolysis, uses a powdered material called ammonia borane, which contains one of the highest hydrogen contents of all solid materials. (Purdue University photo/Andrew Hancock)

 [Download image](#)

WEST LAFAYETTE, Ind. — A new process for storing and generating hydrogen to run fuel cells in cars has been invented by chemical engineers at Purdue University.

The process, given the name hydrothermolysis, uses a powdered chemical called ammonia borane, which has one of the highest hydrogen contents of all solid materials, said Arvind Varma, R. Games Slayter Distinguished Professor of Chemical Engineering and head of the School of Chemical Engineering.

"This is the first process to provide exceptionally high hydrogen yield values at near the fuel-cell operating temperatures without using a catalyst, making it promising for hydrogen-powered vehicles," he said. "We have a proof of concept."

The new process combines hydrolysis and thermolysis, two hydrogen-generating processes that are not practical by themselves for vehicle applications.

Research findings were presented June 15 during the International Symposium on Chemical Reaction Engineering in Philadelphia. The research also is detailed in a paper appearing online in the *AICHE Journal*, published by the American Institute of

Chemical Engineers, and will be published in an

upcoming issue of the journal.

Ammonia borane contains 19.6 percent hydrogen, a high weight percentage that means a relatively small quantity and volume of the material are needed to store large amounts of hydrogen, Varma said.

"The key is how to efficiently release the hydrogen from this compound, and that is what we have discovered," he said.

The paper was written by former Purdue doctoral student Moiz Diwan, now a senior research engineer at Abbott Laboratories in Chicago; Purdue postdoctoral researcher Hyun Tae Hwang; doctoral student Ahmad Al-Kukhun; and Varma. Purdue has filed a patent application on the technology.

In hydrolysis, water is combined with ammonia borane and the process requires a catalyst to generate hydrogen, while in thermolysis the material must be heated to more than 170 degrees Celsius, or more than 330 degrees Fahrenheit, to release sufficient quantities of hydrogen.

However, fuel cells that will be used in cars operate at about 85 degrees Celsius (185 degrees Fahrenheit). Hydrogen fuel cells generate electricity to run an electric motor.

The new process also promises to harness waste heat from fuel cells to operate the hydrogen generation reactor, Varma said.

The researchers conducted experiments using a reactor vessel operating at the same temperature as fuel cells. The process requires maintaining the reactor at a pressure of less than 200 pounds per square inch, far lower than the 5,000 psi required for current hydrogen-powered test vehicles that use compressed hydrogen gas stored in tanks.

In some experiments, the researchers used water containing a form of hydrogen called deuterium. Using water containing deuterium instead of hydrogen enabled the researchers to trace how much hydrogen is generated from the hydrolysis reaction and how much from the thermolysis reaction, details critical to understanding the process.

At the optimum conditions, hydrogen from the hydrothermolysis approach amounted to about 14 percent of the total weight of the ammonia borane and water used in the process. This is significantly higher than the hydrogen yields from other experimental systems reported in the scientific literature, Varma said.

"This is important because the U.S. Department of Energy has set a 2015 target of 5.5 weight percent hydrogen for hydrogen storage systems, meaning available hydrogen should be at least 5.5 percent of a system's total weight," he said. "If you're only yielding, say, 7 percent hydrogen from the material, you're not going to make this 5.5 percent requirement once you consider the combined weight of the entire system, which includes the reactor, tubing, the ammonia borane, water, valves and other required equipment."

The researchers determined that a concentration of 77 percent ammonia borane is ideal for maximum hydrogen yield using the new process.

The research has been funded by the U.S. Department of Energy by a grant through the Energy Center in Purdue's Discovery Park.

Future work on hydrothermolysis will explore scaling up the reactor to the size required for a vehicle to drive 350 miles before refueling. Additional research also is needed to develop recycling technologies for turning waste residues produced in the process back into ammonia borane.

The technology may also be used to produce hydrogen for fuel cells to recharge batteries in portable electronics, such as notebook computers, cell phones, personal digital assistants, digital cameras, handheld medical diagnostic devices and defibrillators.

"The recycling isn't important for small-scale applications, such as portable electronics, but is needed before the process becomes practical for cars," Varma said.

Writer: Emil Venere, 765-494-4709, venere@purdue.edu

Sources: Arvind Varma, (765) 494-4075, avarma@purdue.edu

Jonathan Gortat, innovation strategy manager, Purdue Research Foundation, 765-588-3485, jgortat@purdue.edu

Note to Journalists: An electronic copy of the research paper is available from Emil Venere, 765-494-4709, venere@purdue.edu.

ABSTRACT

Hydrogen Generation from Noncatalytic Hydrothermolysis of Ammonia Borane for Vehicle Applications

Moiz Diwan, Hyun Tae Hwang, Ahmad Al-Kukhun, and Arvind Varma

School of Chemical Engineering, Purdue University

Ammonia borane (AB) is a promising hydrogen storage material as it contains 19.6 wt% hydrogen. In this paper, our recently developed hydrothermolysis approach to release hydrogen is studied over a wide range of AB concentrations (6-88 wt%), at pressure 14.7 and 200 psia, and temperature 85-135°C. It is shown that with increasing AB concentration up to 77 wt%, the H₂ yield increases, and that the role of thermolysis, as compared to hydrolysis, increases. The maximum hydrogen storage capacity, obtained at 77 wt% AB and T_{reactor} ~85°C along with rapid kinetics, was 11.6 and 14.3 wt% at pressure 14.7 and 200 psia, respectively. To our knowledge, on a material basis, the AB hydrothermolysis process is the first one to provide such high hydrogen yield values at near PEM fuel cell operating temperatures without use of catalyst, and thus is promising for use in fuel cell based vehicle applications.

Featured News

- Two Purdue female undergrads race small

airplane across country

- Genome sequence may lead to better methods to target lice
- Undergraduates train at Purdue for national earthquake program
- Military institute awards \$1 million to Indiana schools that help service members, veterans
- Purdue students participate in the 2010 Air Race Classic
- Jerry Lynch named interim Krannert dean
- Purdue Extension storm recovery resources available online

[More News »](#)

Copyright © 2009 Purdue University.
Copyright Infringement Information

Purdue University is an equal access/equal opportunity university

Find something interesting?

Share it! 

Maintained by: UNS
[Offer Feedback](#)